

# INTERNATIONAL STANDARD

**ISO  
13916**

First edition  
1996-08-01

---

## **Welding — Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature**

*Soudage — Lignes directrices pour le mesurage de la température de  
préchauffage, de la température entre passes et de la température de  
maintien du préchauffage*

This material is reproduced from ISO documents under International Organization for Standardization (ISO) Copyright License number IHS/ICC/1996. Not for resale. No part of these ISO documents may be reproduced in any form, electronic retrieval system or otherwise, except as allowed in the copyright law of the country of use, or with the prior written consent of ISO (Case postale 56, 1211 Geneva 20, Switzerland, Fax +41 22 734 10 79), IHS or the ISO Licensor's members.



Reference number  
ISO 13916:1996(E)

## ISO 13916:1996(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 13916 was prepared by the European Committee for Standardization (CEN) in collaboration with ISO Technical Committee TC 44, *Welding and allied processes*, Subcommittee SC 10, *Unification of requirements in the field of metal welding*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

© ISO 1996

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case postale 56 • CH-1211 Genève 20 • Switzerland  
Internet central@isocs.iso.ch  
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

## Contents

|                                                     | page |
|-----------------------------------------------------|------|
| Foreword .....                                      | iv   |
| 1 Scope .....                                       | 1    |
| 2 Definitions .....                                 | 1    |
| 2.1 Preheating temperature ( $T_p$ ) .....          | 1    |
| 2.2 Interpass temperature ( $T_i$ ) .....           | 1    |
| 2.3 Preheat maintenance temperature ( $T_m$ ) ..... | 1    |
| 3 Requirements .....                                | 1    |
| 3.1 Point of measurement .....                      | 1    |
| 3.2 Time of measurement .....                       | 2    |
| 3.3 Test equipment .....                            | 3    |
| 4 Test report .....                                 | 3    |
| 5 Designation .....                                 | 3    |

## Foreword

The text of EN ISO 13916:1996 has been prepared by Technical Committee CEN/TC 121 "Welding", the secretariat of which is held by DS, in collaboration with Technical Committee ISO/TC 44 "Welding and allied processes".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 1997, and conflicting national standards shall be withdrawn at the latest by February 1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

## 1 Scope

This standard specifies requirements for the measurement of preheating temperature, interpass temperature and preheat maintenance temperature for fusion welding. This standard may also be applied as appropriate in the case of other welding processes. This standard does not cover the measurement of post weld heat treatment temperatures.

## 2 Definitions

For the purposes of this standard the following definitions apply:

**2.1 preheating temperature ( $T_p$ ):** the temperature of the workpiece in the weld zone immediately prior to any welding operation. It is normally expressed as a minimum and is usually equal to the minimum interpass temperature.

**2.2 interpass temperature ( $T_i$ ):** the temperature in a multi-run weld and adjacent parent metal immediately prior to the application of the next run. It is normally expressed as a maximum temperature.

**2.3 preheat maintenance temperature ( $T_m$ ):** the minimum temperature in the weld zone which shall be maintained if welding is interrupted.

## 3 Requirements


### 3.1 Point of measurement

The temperature measurement shall normally be made on the surface of the workpiece facing the welder, at a distance of  $A = 4 \times t$ , but not more than 50 mm, from the longitudinal edge of the groove (see figure 1). This shall apply for workpieces thickness  $t$  not exceeding 50 mm in the weld.


When the thickness exceeds 50 mm, the required temperature shall exist in the parent metal for a distance of at least 75 mm or as otherwise agreed in any direction from the joint preparation. Where practicable, the temperature shall be measured on the face opposite to that being heated. Otherwise, the temperature shall be confirmed on the heated face at a time after removal of the heat source related to parent metal thickness to allow for temperature equalization. Where fixed permanent heaters are in use and there is no access to the reverse face for temperature measurement, readings shall be taken on the exposed parent metal surface immediately adjacent to the weld preparation. The time allowed for the temperature equalization shall be of the order of 2 min for each 25 mm of parent metal thickness.

Interpass temperature shall be measured on the weld metal or the immediately adjacent parent metal.

Dimensions in mm



a) butt joint



b) fillet joint

$$t \leq 50: A = 4 \times t, \text{ max. } 50 \text{ mm}$$

$$t > 50: A = 75$$

Figure 1 - Distance between points of measurement

### 3.2 Time of measurement

Interpass temperature shall be measured in the weld area immediately before passage of the arc.

If the preheat maintenance temperature is specified it shall be monitored during the period of welding interruption.

### 3.3 Test equipment

Equipment used for temperature measurement should be specified in the welding procedure specifications, e.g.:

- temperature sensitive materials (e.g. crayons or paints) (TS);
- contact thermometer (CT);
- thermocouple (TE);
- optical or electrical devices for contactless measurement (TB).

### 4 Test report

If a test report is required, it shall refer to this standard and give the following minimum information in accordance with the specification in welding procedure specification:

- measured preheating temperature, in °C;
- measured interpass temperature, in °C;
- measured preheat maintenance temperature, in °C;
- any deviation from this standard, if applicable.

### 5 Designation

Examples of designation, which should be used in test reports

#### 5.1 Example 1

A preheating temperature  $T_p$  measured only once in accordance with this standard as 155 °C ( $T_p$  155) using a contact thermometer (CT) shall be designated as follows:

Temperature EN ISO 13916 -  $T_p$  155 - CT

#### 5.2 Example 2

An interpass temperature  $T_i$  measured more than once in accordance with this standard as 130 °C, 153 °C and 160 °C ( $T_i$  130/160) using a thermocouple (TE) shall be designated as follows:

Temperature EN ISO 13916 -  $T_i$  130/160 - TE

---

---

**ICS 25.160.10**

**Descriptors:** welding, fusion welding, workpieces, heat affected zone, temperature, temperature measurements.

Price based on 3 pages

---

---